

This page is mainly introduced the A 958 Grade SC 4130 Class 70/36 chemical information, mechanical properties, physical properties, mechanical properties, heat treatment, and Micro structure, etc. It also contains the use of A 958 Grade SC 4130 Class 70/36, such as it is commonly used in bars, sheet, plates, steel coils, steel pipes, forged and other materials application.

Data Table for Grades Stainless Steels A 958 Grade SC 4130 Class 70/36

A 958 Grade SC 4130 Class 70/36 Standard Number:

ITEM	Standard Number	Descriptions
1	A 958/A 958M (2010)	Standard Specification for Steel Castings, Carbon and Alloy, with Tensile Requirements, Chemical Requirements Similar to Standard Wrought Grades

A 958 Grade SC 4130 Class 70/36 Chemical composition (mass fraction) (wt.%)

Chemical	Min.(%)	Max.(%)
C		0.15
Si		1.00
Mn	3.75	4.75
P		0.045
S		0.03
Ni	9.00	10.50
Cr	19.00	22.00
Al		
Cu		
Ti		
Fe		
N		
Mo		
V		

A 958 Grade SC 4130 Class 70/36 Physical Properties

Tensile strength	115-234	σ_b /MPa
Yield Strength	23	$\sigma_{0.2} \geq$ /MPa
Elongation	65	$\delta_5 \geq$ (%)

ψ	-	$\psi \geq (\%)$
Akv	-	Akv $\geq J$
HBS	123-321	-
HRC	30	-

A 958 Grade SC 4130 Class 70/36 Mechanical Properties

Tensile strength	231-231	σ_b/MPa
Yield Strength	154	$\sigma_{0.2} \geq/MPa$
Elongation	56	$\delta 5 \geq (\%)$
ψ	-	$\psi \geq (\%)$
Akv	-	Akv $\geq J$
HBS	235-268	-
HRC	30	-

A 958 Grade SC 4130 Class 70/36 Heat Treatment Regime

Annealing	Quenching	Tempering	Normalizing	Q & T
√	√	√	√	√

A 958 Grade SC 4130 Class 70/36 Range of products

Product type	Products	Dimension	Processes	Deliver Status
Plates / Sheets	Plates / Sheets	0.08-200mm(T)*W*L	Forging, hot rolling and cold rolling	Annealed, Solution and Aging, Q+T, ACID-WASHED, Shot Blasting
Steel Bar	Round Bar, Flat Bar, Square Bar	Φ8-1200mm*L	Forging, hot rolling and cold rolling, Cast	Black, Rough Turning, Shot Blasting,
Coil / Strip	Steel Coil /Steel Strip	0.03-16.0x1200mm	Cold-Rolled & Hot-Rolled	Annealed, Solution and Aging, Q+T, ACID-WASHED, Shot Blasting
Pipes / Tubes	Seamless Pipes/Tubes, Welded Pipes/Tubes	OD:6-219mm x WT:0.5-20.0mm	Hot extrusion, Cold Drawn, Welded	Annealed, Solution and Aging, Q+T, ACID-WASHED

We can produce Stainless Steels the specifications follows:

Note:

- (1) listed in the table apex diameter (d), to steel thickness (a) multiples said.
- (2) in the ASTM A6 standard specified scope can meet any additional conditions.
- (3) from the standard for 50 mm (2 in).

Mechanical properties

Mechanische Eigenschaften**Caracteristiques mecaniques****ReH Minimum yield strength / Mindestwert der oberen Streckgrenze / Limite d'élasticite minimale****Rm Tensile strength / Zugfestigkeit / Resistance a la traction****A Minimum elongation / Mindestwert der Bruchdehnung / Allongement minimal****J Notch impact test / Kerbschlagbiegeversuch / Essai de flexion par choc****Round bar:****Diameter : 1mm-2000mm****Square bar:****Size: 50mm * 50mm-600mm *600mm****Plate steel/flat bar:****Size: Thickness: 0.1mm-800mm Width: 10mm to 1500mm****Tube/pipe:****Size: OD: 6-219mm WT: 1-35 mm.****Cold-rolled sheet: Thickness: 2-5mm Width:1000mm Length: 2000mm****Hot-rolled sheet: Thickness:6-80mm Width: 210-610mm****Length: We can supply any length based on the customer's requirement.****Forging/hot rolling/ extrusion of steel.****Forging: Shafts with flanks/pipes/tubes/slugs/donuts/cubes/other shapes****Finished goods condition: hot forging/hot rolling + annealing/normalizing + tempering/quenching + tempering/any conditions based on the customer's requirement****Surface conditions: scaled (hot working finish)/ground/rough machining/fine machining/based on the customer's requirement****Furnaces for metallurgical processing: electrode arc + LF/VD/VOD/ESR/Vacuum consumable electrode.****Ultrasonic inspection: 100% ultrasonic inspection for any imperfections or based on the customer's requirement.****UTS according to SEP 1921 C/c,D/d,E/e;A388 or GB/T 6402****Excellent service for all kinds of industries, with advantages of technologies, equipment and price.****We serve you with our honesty, integrity, and professionalism.**